

The
United
States
of
America



**The Director of the United States
Patent and Trademark Office**

Has received an application for a patent for a new and useful invention. The title and description of the invention are enclosed. The requirements of law have been complied with, and it has been determined that a patent on the invention shall be granted under the law.

Therefore, this

United States Patent

Grants to the person(s) having title to this patent the right to exclude others from making, using, offering for sale, or selling the invention throughout the United States of America or importing the invention into the United States of America, and if the invention is a process, of the right to exclude others from using, offering for sale or selling throughout the United States of America, or importing into the United States of America, products made by that process, for the term set forth in 35 U.S.C. 154(a)(2) or (c)(1), subject to the payment of maintenance fees as provided by 35 U.S.C. 41(b). See the Maintenance Fee Notice on the inside of the cover.

David J. Kyros

Director of the United States Patent and Trademark Office



US007772358B2

(12) **United States Patent**
Tang et al.

(10) **Patent No.:** **US 7,772,358 B2**
(45) **Date of Patent:** **Aug. 10, 2010**

(54) **POLYTRIAZOLES CONSTRUCTED BY
1,3-DIPOLAR CYCLOADDITION**

(75) Inventors: **Benzhong Tang**, Hong Kong (CN);
Anjun Qin, Hong Kong (CN); **Matthias
Haeussler**, Bad Lauchstaedt (DE)

(73) Assignee: **The Hong Kong University of Science
and Technology**, Hong Kong (CN)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

(21) Appl. No.: **11/896,675**

(22) Filed: **Sep. 5, 2007**

(65) **Prior Publication Data**

US 2008/0103273 A1 May 1, 2008

Related U.S. Application Data

(60) Provisional application No. 60/842,371, filed on Sep.
6, 2006.

(51) **Int. Cl.**

C08G 73/08 (2006.01)

C07C 247/02 (2006.01)

C07C 247/16 (2006.01)

(52) **U.S. Cl.** **528/268**; 528/422; 528/423;
552/8; 552/11; 544/180

(58) **Field of Classification Search** 526/204,
526/261; 548/255, 256, 257; 552/8, 11;
544/180; 528/268, 422-423

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,665,246 A * 5/1987 Anderson 585/320
5,681,904 A * 10/1997 Manzara 525/404
7,009,059 B2 3/2006 Wurziger et al.
7,109,359 B1 * 9/2006 Dave et al. 552/11
2005/0197334 A1 * 9/2005 Wang et al. 514/227.5
2005/0203147 A1 * 9/2005 Zhou et al. 514/340
2005/0222427 A1 10/2005 Sharpless et al.
2006/0247410 A1 * 11/2006 Tang et al. 528/86
2007/0176164 A1 * 8/2007 Sato et al. 257/40
2008/0311412 A1 * 12/2008 Fokin et al. 428/457

FOREIGN PATENT DOCUMENTS

WO WO 2005085176 A1 * 9/2005

OTHER PUBLICATIONS

Diaz et al. Click Chemistry in Materials Synthesis. 1. Adhesive
Polymers from Copper-Catalyzed Azide-Alkyne Cycloaddition.
Published Online (Wiley InterScience) Jul. 28, 2004. Journal of
Polymer Science: Part A: Polymer Chemistry, 2004, vol. 42, pp.
4392-4403.*

Diaz et al. Click Chemistry in Materials Synthesis. 1. Adhesive
Polymers from Copper-Catalyzed Azide-Alkyne Cycloaddition.
Proof of publication date of Jul. 28, 2004. Wiley InterScience.*

Pigge et al. An Enaminone-Directed Benzannulation/Macrocycliza-
tion Approach to Cyclophane Ring Systems. J. Org. Chem., 2002, 67,
pp. 4547-4552.*

Zhang et al. (Ruthenium-Catalyzed Cycloaddition of Alkynes and
organic Azides. Journal of the American Chemical Society. Oct. 28,
2005. pp. 15998-15999).*

Qin et al. (Synthesis of a Hyperbranched Polytriazole by 1,3-Dipolar
Polycycloaddition. Polymer Preprints. 2006, 47(2), pp. 681-682).*

Katritzky et al. (Triazole-oligomers by 1,3-dipolar cycloaddition.
ARKIVOC 2006 (v), pp. 43-62).*

Rodionov et al. (Mechanism of the Ligand-Free Cu(I)-Catalyzed
Azide-Alkyne Cycloaddition Reaction. Angew. Chem. Int. Ed. 2005,
44, pp. 2210-2215).*

Katritzky et al. (Synthesis of C-Carbamoyl-1,2,3-triazoles by Micro-
wave-Induced 1,3-Dipolar Cycloaddition of Organic Azides to
Acetylenic Amides. J. Org. Chem., 2002, 67 (25). p. 9077-9079).*

Durden et al. (The Reaction of Azidoorganic Compounds with Acety-
lenes. Journal of Chemical Engineering Data. Apr. 1, 1964. pp. 228-
232).*

Haeussler et al. (Synthesis and properties fo hyperbranched
organometallic polyyenes and poly(aroylarylene)s and their utiliza-
tion in photolithographic patterning. PMSE Preprints. 2005, 93, pp.
869-871).*

Anonymous (1,3-Dipolar Cycloaddition to Acetylenic Compounds:
New Thermosets for Electronics Packaging. ip.com. Mar. 1, 2005).*

Helms, B., et al., "Dendronized Linear Polymers via 'Click Chem-
istry'", J. Am. Chem. Soc., vol. 126, pp. 15020-15021, (2004).

Englert, B.C., et al., "Click Chemistry as a Powerful Tool for the
Construction of Functional Poly(p-phenyleneethynylene)s: Com-
parison of Pre- and Postfunctionalization Schemes", Macromol-
ecules, vol. 38, pp. 5868-5877, (2005).

(Continued)

Primary Examiner—Milton I Cano

Assistant Examiner—Briann R Fink

(74) Attorney, Agent, or Firm—The Nath Law Group

(57) **ABSTRACT**

A process of synthesizing hyperbranched polytriazoles, lin-
ear and hyperbranched poly(aroyltriazoles) by Huisgen 1,3-
dipolar cycloaddition. The polytriazoles were prepared by
A₂+B₃ method to avoid self-polymerization during monomer
preparation and storage. The polymers are light emissive and
can be crosslinked to generate well-resolution photopatterns
upon UV irradiation. White light emission patterns were
observed with fluorescence microscopy. The high molecular
weight poly(aroyltriazoles) (up to 26000 Da) are prepared in
high yields (up to 92.0%) and with high regioselectivity (the
ratio of 1,4- and 1,5-disubstituted 1,2,3-triazole is equal or
larger than 9:1). The polycyclomerization is not moisture or
oxygen sensitive and therefore, no special precautions are
necessary before and during the reaction. All the polymers are
processable, easily film-forming, and curable into thermosets
by heat or irradiation. The hyperbranched polymers can act as
fluorescent adhesive materials with large tensile strength.

18 Claims, 11 Drawing Sheets

OTHER PUBLICATIONS

Binder, W.H., et al., "Combining Ring-Opening Metathesis Polymerization (ROMP) with Sharpless-Type 'Click' Reactions: An Easy Method for the Preparation of Side Chain Functionalized Poly(oxynorbornenes)", *Macromolecules*, vol. 37, pp. 9321-9330, (2004).

Tsarevsky, N.V., et al., "Step-Growth 'Click' Coupling of Telechelic Polymers Prepared by Atom Transfer Radical Polymerization", *Macromolecules*, vol. 38, pp. 3558-3561, (2005).

Scheel, A.J., et al., "Novel Hyperbranched Poly([1,2,3]-triazole)s Derived from AB₂ Monomers by a 1,3-Dipolar Cycloaddition", *Macromol. Rapid Commun.*, vol. 25, pp. 1175-1180, (2004).

Rostovtsev, V.V., et al., "A Stepwise Huisgen Cycloaddition Process: Copper(I)-Catalyzed Regioselective 'Ligation' of Azides and Terminal Alkynes", *Angew. Chem. Int. Ed.*, vol. 41, pp. 2596-2599, (2002).

Van Steenis, D.J.V.C., et al., "Click-chemistry as an efficient synthetic tool for the preparation of novel conjugated polymers", *Chem. Commun.*, pp. 4333-4335, (2005).

* cited by examiner

Figure 1




Figure 2




Figure 3




Figure 4




Figure 5




Figure 6




Figure 7




Figure 8




Figure 9




Figure 10





Figure 11



POLYTRIAZOLES CONSTRUCTED BY 1,3-DIPOLAR CYCLOADDITION

CROSS-REFERENCE TO RELATED APPLICATIONS

This application claims the benefit of U.S. Provisional Patent Application No. 60/842,371, filed Sep. 6, 2006, the contents of which are hereby incorporated by reference in their entirety.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present disclosure relates to the synthesis of linear and hyperbranched polytriazoles by fast and region-selective 1,3-dipolar cycloaddition of organic azides and acetylenes by metal-free thermal methodology.

2. Related Art

The unique molecular structures of polytriazoles render them with novel features, such as for use with respect to photoresist and light emission. There are many publications that disclose linear polytriazoles, which were obtained by Cu(I)-catalyzed 1,3-dipolar cycloaddition reaction (for examples: Helms, B.; Mynar, J. L.; Hawker, C. J.; Fréchet, J. M. J. *J. Am. Chem. Soc.* 2004, 126, 15020. (b) Englert, B. C.; Bakbak, S.; Bunz, H. F. *Macromolecules*, 2005, 38, 5868. (c) Binder, W. H.; Kluger, C. *Macromolecules*, 2004, 37, 9321. (d) Tsarevsky, N. V.; Sumerlin, B. S.; Matyjaszewski K. *Macromolecules*, 2005, 38, 3558). But when the conditions disclosed conditions are applied for the synthesis of hyperbranched polymers, partially soluble or totally insoluble materials are always obtained (Scheel, A. J.; Komber, H.; Voit, B. I. *Macromol. Rapid. Commun.* 2004, 25, 1175), which prohibits investigation of the resultant materials and their practical applications.

After Huisgen's comprehensive review in 1984 (Huisgen, R. In *1,3-Dipolar Cycloaddition Chemistry*; Padwa, A., Ed.; Wiley: New York, 1984), the research on 1,3-dipolar cycloaddition reactions remained silent until Sharpless and coworkers recognized the potential application and found an efficient method to synthesize the regioselective 1,2,3-triazoles from organic azides and terminal acetylenes by Cu(I) catalysts. (V. V. Rostovtsev, L. G. Green, V. V. Ivin, K. B. Sharpless *Angew. Chem. Int. Ed.* 2002, 41, 2596; and K. B. Sharpless, US 2005/0222427 A1). Due to its high yield and high regioselectivity, they defined this methodology as "Click Chemistry". This breakthrough aroused tremendous interest among scientists in particular for the construction of bio-conjugated materials and only limited reports have addressed electro-optical macromolecular materials (D. J. V. C. Steenis, O. R. P. David, G. P. F. Strijdonck, J. H. Maarseveen, J. N. H. Reek *Chem. Commun.* 2005, 4333).

Because of their substantially globular molecular architectures, hyperbranched polymers are envisioned to exhibit novel properties such as low viscosity and high thermal stability and serve as functional materials. Moreover, the synthesis of hyperbranched polymers can be done in a one-pot single-step procedure. Realization of the full potential of hyperbranched polymers calls for the exploration of new, versatile methods for their syntheses.

Schell, et al. reported for the first time hyperbranched polymers constructed by either Cu(I)-catalyzed or thermal 1,3-dipolar cycloadditions of AB₂ type monomers (where A represents one azide group and B₂ represents two acetylenes, all in one organic molecule; Scheel, A. J.; Komber, H.; Voit, B. I. *Macromol. Rapid. Commun.* 2004, 25, 1175). This meth-

odology contains some disadvantages, which limit its practical applicability. Soluble hyperbranched polymers can only be obtained when the Cu(I) catalyzed 1,3-dipolar cycloaddition is performed in highly polar solvents (such as DMSO or DMF), which are difficult to remove after polymerization. Another problem is the self-polymerization of this type of monomer when stored for long time under ambient conditions.

Steenis et al. reported the light emission properties of linear polytriazoles prepared by Cu(I)-catalyzed 1,3-dipolar cycloaddition with conjugated diazides and diacetylenes. However, this methodology requires a long reaction time (up to 170 h) and may hamper again its usage when employed in practical applications. Most of the other linear polymers containing 1,2,3-triazole moieties (B. Helms, *J. Am. Chem. Soc.* 2004, 126, 15020; B. C. Englert, *Macromolecules*, 2005, 38, 5868; W. H. Binder, *Macromolecules*, 2004, 37, 9321; N. V. Tsarevsky, *Macromolecules*, 2005, 38, 3558) are again only soluble in high polar solvents, such as DMF and DMSO, which is very inconvenient for investigations of their properties and further processing.

Wurziger et al. (U.S. Pat. No. 7,009,059) reported the 1,3-dipolar cycloaddition between azides and acetylenes groups of mainly low molecular weight compounds in microreactors. Manzara (U.S. Pat. No. 5,681,904) reported cross-linked polymers. The author adopted 1,3-dipolar cycloaddition between polymers containing azido groups either in the main chain or as pendants and diacetylenic esters or amides. The resulting polymers were insoluble and the inventor did not provide any information of the regioselectivity of the product.

It is known that aroylacetylenes can be cyclotrimerized when refluxed in DMF or in mixtures with other solvents such as toluene for a long time (*J. Org. Chem.* 2002, 67, 4547). The inventors have abundant experiences on the polycyclotrimerization of aroylacetylene monomers (Dong, H. C.; Zheng, R. H.; Lam, J. W.-Y.; Haeussler, M.; Qin, A. J.; Tang, B. Z. *Macromolecules*, 2005, 38, 6382-6391).

Further, compounds with azido moieties can form active radicals when irradiated with UV light (Bräse, S.; Gel, C.; Knepper, K.; Zimmermann, V. *Angew. Chem. Int. Ed.* 2005, 44, 5188).

SUMMARY OF THE INVENTION


The present subject matter addresses the above concerns by teaching the following processes and products.

The present disclosure includes a process for the synthesis of polytriazoles. The process includes reacting separate azide monomers and acetylene monomers by 1,3-dipolar cycloaddition. Polymerization occurs by refluxing said monomers in an organic solvent for a set period of time.

In some aspects, the polytriazole is a hyperbranched polytriazole or a hyperbranched poly(aroyltriazole) that is synthesized by the reaction of a di-monomer and a tri-monomer, where one of the azide monomers and acetylene monomers is a di-monomer and the other monomer is a tri-monomer.


In some aspects, the acetylene monomer used in the synthesis of the hyperbranched polytriazole or the hyperbranched poly(aroyltriazole) is a diacetylene, an aromatic diacetylene, a conjugated diacetylene, a triyne, an aromatic triyne, a conjugated triyne, or an aroyldiacetylene. In some aspects, the acetylene monomer used in the synthesis of the hyperbranched polytriazole or the hyperbranched poly(aroyltriazole) has formula I, II, III, or IV:

3




These are non-limiting examples, however, and other acetylene monomers may be used.

In some aspects, the R_1 group of formula I or formula II is a



In some aspects, the R_4 group of formula III or formula IV is a

4





In some aspects, the R group is hydrogen, an alkyl, a vinyl, an acetyl, an aryl or a heteroaryl. In some aspects, $m \geq 1$.

In some aspects, the azide monomer used in the synthesis of the hyperbranched polytriazole or the hyperbranched poly (aryltriazole) is a diazide, a conjugated diazide, a nonconjugated diazide, a triazide, a conjugated triazide, nonconju-




5

gated triazide, a metal containing diazide, a metal containing conjugated diazide, a metal containing nonconjugated diazide, a metal containing triazide, a metal containing conjugated triazide, or a metal containing nonconjugated triazide. In some aspects, the azide monomer used in the synthesis of the hyperbranched polytriazole or the hyperbranched poly (aryltriazole) has formula V or VI:







These are non-limiting examples, however, and other azide monomers may be used.

In some aspects, the R_2 group of formula V is a






In some aspects, the Ar group is a



In some aspects, $m \geq 1$.


6

In some aspects, the R_3 group of formula VI is a



35 In some aspects, X is hydrogen, an alkyl, a vinyl, an acetyl, an aryl, a heteroaryl, or a halogen. In some aspects, the R group is hydrogen, an alkyl, a vinyl, an acetyl, an aryl, or a heteroaryl. These are non-limiting examples, however, and other groups may be used.


40 In some aspects, the polytriazole is a hyperbranched polytriazole which has the formula VII:




65 This is a non-limiting example, however, and other hyperbranched polytriazoles may be formed.

7


In some aspects, the R₁ group of formula VII is a



In some aspects, the R₂ group of formula VII is a




In some aspects, the Ar group is a




8

-continued




In some aspects, the R group is hydrogen, an alkyl, a vinyl, an acetyl, an aryl, or a heteroaryl. In some aspects, $m \geq 1$. These are non-limiting examples, however, and other groups may be used.

In some aspects, the polytriazole is a hyperbranched polytriazole which has the formula VIII:




This is a non-limiting example, however, and other hyperbranched polytriazoles may be formed.

In some aspects, the R_3 group of formula VIII is a











9





In some aspects, X is hydrogen, an alkyl, a vinyl, an acetyl, an aryl, a heteroaryl, or a halogen. In some aspects, the R group is hydrogen, an alkyl, a vinyl, an acetyl, an aryl, or a heteroaryl. These are non-limiting examples, however, and other groups may be used.

In some aspects, the R_4 group of formula VIII is a




10




In some aspects, the R group is hydrogen, an alkyl, a vinyl, an acetyl, an aryl or a heteroaryl. In some aspects, $m \geq 1$. These are non-limiting examples, however, and other groups may be used.

In some aspects, the polytriazole is a hyperbranched poly (aryltriazole) which has the formula IX or X:

(IX)




(X)





11

This is a non-limiting example, however, and other hyper-branched poly(aryltriazoles) may be formed.


In some aspects, the R_1 group of formula IX is a



In some aspects, the R_2 group of formula IX is a




In some aspects, the Ar group is a




12

-continued




In some aspects, the R group is hydrogen, an alkyl, a vinyl, an acetyl, an aryl, or a heteroaryl. In some aspects, $m \geq 1$. These are non-limiting examples, however, and other groups may be used.

In some aspects, the R_3 group of formula X is a




In some aspects, X is hydrogen, an alkyl, a vinyl, an acetyl, an aryl, a heteroaryl, or a halogen. In some aspects, the R group is hydrogen, an alkyl, a vinyl, an acetyl, an aryl, or a heteroaryl. These are non-limiting examples, however, and other groups may be used.

In some aspects, the R_4 group of formula X is a




13



In some aspects, the R group is hydrogen, an alkyl, a vinyl, an acetyl, an aryl or a heteroaryl. In some aspects, $m \geq 1$. These are non-limiting examples, however, and other groups may be used.




In some aspects, the polytriazole is a linear poly(aroyltriazole) that is synthesized by the reaction of a diazide monomer and an aroyldiacetylene monomer. In some aspects, the diazide monomer used in the synthesis of the linear poly(aroyltriazole) is a conjugated diazide, a nonconjugated diazide, a metal containing diazide, a metal containing conjugated diazide, or a metal containing nonconjugated diazide. In some aspects, the diazide monomer used in the synthesis of the linear poly(aroyltriazole) has formula XI:







(XI)

14

This is a non-limiting example, however, and other diazide monomers may be used. In some aspects, the R_2 group of formula XI is a




In some aspects, the Ar group is a



In some aspects, the R group is hydrogen, an alkyl, a vinyl, an acetyl, an aryl, or a heteroaryl. In some aspects, $m \geq 1$. These are non-limiting examples, however, and other groups may be used.


In some aspects, the aroyldiacetylene monomer used in the synthesis of the linear poly(aroyltriazole) has formula XII:

(XII)



This is a non-limiting example, however, and other aroyldiacetylene monomers may be used. In some aspects, the R_4 group of formula XII is a

15



In some aspects, the R group is hydrogen, an alkyl, a vinyl, an acetyl, an aryl or a heteroaryl. In some aspects, $m \geq 1$. These are non-limiting examples, however, and other groups may be used.

In some aspects, the organic solvent used in the synthesis of the polytriazoles is selected from 1,4-dioxane, dimethylfor-

16

amide and toluene. These are non-limiting examples, however, and other organic solvents may be used.

In some aspects, the polymerization of the hyperbranched polytriazoles occurs within a time range of about 70 hours to about 90 hours, or from a range of about 82 to about 88 hours. These are non-limiting examples, however, and other ranges may be used.

In some aspects, the polymerization of the hyperbranched poly(aroyltriazoles) and the linear poly(aroyltriazoles) occurs within a time range of about 4 hours to about 6 hours, more particularly about 5 hours. This is a non-limiting example, however, and other ranges may be used.

BRIEF DESCRIPTION OF THE FIGURES

FIG. 1 shows the effect of monomer concentration [M] on the 1,3-dipolar cycloaddition of tris(4-ethynylphenyl)amine and 1,4-bis(4-azidobutoxy)benzene in 1,4-dioxane under reflux for 72 hours; the molar ratio of triyne and diazide is 2:3.

FIG. 2 shows the IR spectra of monomers (A) tris(4-ethynylphenyl)amine and (B) 1,4-bis(4-azidobutoxy)benzene and their hyperbranched polymers (C) PI and (D) PII.

FIG. 3 shows the ^1H NMR spectra of monomers (A) tris(4-ethynylphenyl)amine and (B) 1,4-bis(4-azidobutoxy)benzene, model compounds (C) tris(4-(1-(4-phenoxybutyl)-1H-1,2,3-triazol-4-yl)phenyl)amine and (D) tris(4-(3-(4-phenoxybutyl)-3H-1,2,3-triazol-4-yl)phenyl)amine, and (E) hyperbranched polymer PI in $\text{DMSO}-d_6$. The solvent and water peaks are marked with asterisks (*).

FIG. 4 shows the ^1H NMR spectra of monomers (A) tris(4-ethynylphenyl)amine and (B) 1,4-bis(6-azidoheptyloxy)benzene, model compounds (C) tris(4-(1-(6-phenoxyhexyl)-1H-1,2,3-triazol-4-yl)phenyl)amine and (D) tris(4-(3-(6-phenoxyhexyl)-3H-1,2,3-triazol-4-yl)phenyl)amine, and (E) hyperbranched polymer PII in $\text{DMSO}-d_6$. The solvent and water peaks are marked with asterisks (*).

FIG. 5 shows the TGA thermographs of hyperbranched polymers PI and PII recorded under nitrogen at a heating rate of 20°C./min .

FIG. 6 shows the absorption and emission spectra of DCM solutions ($\sim 1.5 \times 10^{-3} \text{ mg/mL}$) and thin solid films of (A) PI and (B) PII. Excitation wavelength: 337 nm (DCM) and 340 (film).

FIG. 7 shows photoresist patterns generated by photocross-linking of PI for 5 min in air; images taken under (A) normal room lighting and (B) UV lamp illumination.

FIG. 8 shows the IR spectra of PI (A) before and (B) after UV irradiation for 5 min.

FIG. 9 shows the IR spectra of PII (A) before and (B) after UV irradiation for 5 min.

FIG. 10 shows the change of absorption spectra of (A) PI and (B) PII with time of UV irradiation (365 nm). Insert: plot of A/A_0 of (A) PI and (B) PII at $\sim 340 \text{ nm}$ with irradiation time (t) (A_0 =Absorbance intensity at 0 min).

FIG. 11 shows the UV and PL spectra of polymer PXII in different polar solvents (conc. $5.4 \mu\text{g/mL}$). Excitation wavelength: 390 nm.



DETAILED DESCRIPTION

The present disclosure includes a process of producing novel readily soluble hyperbranched polytriazoles by 1,3-dipolar cycloaddition. The soluble hyperbranched polytriazoles are constructed by diazides and triynes or diacetylenes and triazides monomers. When aroyldiacetylenes are reacted under metal-free 1,3-dipolar cycloaddition conditions with di- or tri-azide monomers, highly regioselective linear and

17

hyperbranched poly(aryltriazole)s can be achieved in excellent yields and with high molecular weights. The separated acetylene and azide monomers efficiently prohibit undesired self-polymerization during monomer preparation and storage.

The present disclosure includes a process of preparing soluble, and therefore processible, hyperbranched poly(triazoles) and poly(aryltriazoles) as shown in Schemes (i) and (ii) as well as linear poly(aryltriazoles) from diacetylenes and diazides as shown in Scheme (iii).




18


-continued

R₁ =

5



1



2

15

20

3

15

20

3

25

30

35

40

45

50

55

60

65

70

75

80

85

90

95

100

105

110

115

120

125

130

140

145

150

155

160

165

170

175

180

185

190

195

200

205

210

215

220

225

230

235

240

245

250

255

260

265

270

275

280

285

290

295

300

305

310

315

320

325

330

335

340

345

350

355

360

365

370

375

380

385

390

395

400

405

410

415

420

425

430

435

440

445

450

455

460

465

470

475

480

485

490

495

500

505

510

515

520

525

530

535

540

545

550

555

560

565

570

575

580

585

590

595

600

605

610

615

620

625

630

635

640

645

650

655

660

665

670

675

680

685

690

695

700

705

710

715

720

725

730

735

740

745

750

755

760

765

770

775

780

785

790

795

800

805

810

815

820

825

830

835

840

845

850

855

860

865

870

875

880

885

890

895

900

905

910

915

920

925

930

935

940

945

950

955

960

965

970

975

980

985

990

995

1000

1005

1010

1015

1020

1025

1030

1035

1040

1045

1050

1055

1060

1065

1070

1075

1080

1085

1090

1095

1100

1105

1110

1115

1120

1125

1130

1135

1140

1145

1150

1155

1160

1165

1170

1175

1180

1185

1190

1195

1200

1205

1210

1215

1220

1225

1230

1235

1240

1245

1250

1255

1260

1265

1270

1275

1280

1285

1290

1295

1300

1305

1310

1315

1320

1325

1330

1335

1340

1345

1350

1355

1360

1365

1370

1375

1380

1385

1390

1395

1400

1405

1410

1415

1420

1425

1430

1435

1440

1445

1450

1455

1460

1465

1470

1475

1480

1485

1490

1495

1500

1505

1510

1515

1520

1525

1530

1535

1540

1545

1550

1555

1560

1565

1570

1575

1580

1585

1590

1595

1600

1605

1610

1615

1620

1625

1630

1635

1640

1645

1650

1655


1660

1665

1670

19


-continued




20

-continued


(ii)



21



(iii)

R₂ = 5-8 R₄ = 12-21

where R represents a proton (R=H) or any organic groups (e.g. R=alkyl, vinyl, acetyl, aryl, heteroaryl), and m \geq 1. X presents a proton (X=H), or any organic groups (e.g. X=alkyl, vinyl, acetyl, aryl, heteroaryl), or halogen atom (X=F, Cl, Br, I).

This subject matter is not limited to the monomer and polymer structures listed in schemes (i)-(iii). However, acetylene, especially the aroylacetylene groups, are preferentially connected to aromatic or other conjugated structural units. The azide monomers can be conjugated and nonconjugated compounds.

One objective of this subject matter is to prepare functional hyperbranched polytriazoles by 1,3-dipolar cycloaddition reaction with functional monomers of azides and acetylenes in an optimized reaction condition (FIG. 1). This method employs a strategy of separated azides and acetylenes functionalities in order to avoid undesired self-polymerization during monomer synthesis and storage. The obtained hyperbranched polytriazoles are readily soluble in common organic solvents, such as chloroform, tetrahydrofuran and dichloromethane. The obtained hyperbranched polytriazoles possess both azide and acetylene periphery as observed from their IR spectra (FIG. 2). The ratio of 1,4- and 1,5-disubstituted 1,2,3-triazole are calculated from their proton NMR comparing with that of their model compounds (FIG. 3 and FIG. 4). The obtained hyperbranched polytriazoles also have high thermal stabilities (FIG. 5) and can emit light upon excitation (FIG. 6). The polymers can be crosslinked by thermal and radiation methods. It is possible to take advantage of the crosslinkable properties of the unreacted azide groups on the periphery of the polymers. UV irradiation, through a negative mask and followed by dissolution of the unexposed materials, can generate light emissive patterns and thus, make the polymers ideal candidates for the application in the manufacture of integrated circuits and other high-tech utilities.

Furthermore, aroylacetylenes react with azides to produce highly regioselective linear and hyperbranched poly(aroyltriazole)s. The regioselectivity of the 1,4- and 1,5-disubstituted 1,2,3-triazoles (>9:1) is much higher than the normal ratio (1:1) obtained from conventional thermal 1,3-dipolar

22

cycloaddition (Huisgen, R. In *1,3-Dipolar Cycloaddition Chemistry*; Padwa, A., Ed.; Wiley: New York, 1984)). There are three main features of this type of cycloaddition: (1) it requires a short reaction time, (2) it does not require strict experimental precautions in order to exclude oxygen and moisture from the reaction mixture, and (3) this reaction is a metal-free catalyzed system, which renders it environmental friendly, economically and without any catalyst residues left inside the polymer.

All the obtained polytriazoles exhibit interesting optical and thermal properties, which can be readily tuned by incorporating of functional features such as various types of chromophores into the linear and hyperbranched poly(aroyl)triazole structures. Such polymers may be useful as electro-optical materials.

This subject matter is concerned with two types of structural polymers, one of which are hyperbranched polytriazoles constructed from triyne and diazide monomers or triazide and diacetylene monomers, and the others are linear and hyperbranched poly(aroyltriazoles) prepared from the respective di- and tri-functionalized monomers.

The first part of this subject matter, the thermal 1,3-dipolar cycloaddition between triynes and diazides or triazides and diacetylenes can achieve soluble and processible hyperbranched polytriazoles with high yields (up to 75.7%) and molecular weights up to 20,000 Daltons under optimized reaction conditions, such as the comonomer ratios, monomer concentrations, reaction time, and reaction temperature. Upon UV excitation, the polymers PI and PII (Chart 1) can emit strong blue lights with high quantum yields in dichloromethane (the data are listed in Table 1). Further, the polytriazoles with strong acceptor units such as the 1,2,3-triazoles are potential candidates for electron transporting materials in electronic devices.

According to the proposed mechanism of this reaction, the second part of this subject matter is to capture the intermediates by reacting with more active azides compounds. A highly regioselective product is thus obtained when 1-phenylprop-2-yn-1-one is reacted with 1-(azidomethyl)benzene as a model reaction. The ratio of 1,4- and 1,5-disubstituted 1,2,3-triazole is determined larger than 10/1. The isolated yield of 1,4-disubstituted 1,2,3-triazole compound is as high as 90.5%. The aroylacetylenes have some advantages over the pure acetylenes: shorter reaction time (4-6 h), higher regioselectivity and higher conversion of the monomers and, consequently, higher yield of the resulting polymers. Furthermore, this reaction does not require any precautions to exclude moisture or oxygen as other synthetic protocols for click chemistry. Different aroyldiacetylenes were treated with different diazides in a DMF/toluene solvent mixture. Delightfully, readily soluble linear poly(aroyltriazoles) are obtained in high yields (up to 92%) and with high molecular weight (the data are listed in Table 3). From the proton NMR spectra, the ratio of 1,4- to 1,5-disubstituted 1,2,3-triazole inside the polymers are all deduced to about 9/1.

The luminescent polymers contain numerous of these functionalities on the periphery and thus were utilized for the fabrication of photoresist patterns. The polymers cross-link upon irradiation in air. After washing away the unexposed part, well-resolved 3-dimensional patterns were generated (FIG. 7A). When observed under fluorescence optical microscope, white light patterns were obtained at excitation wavelengths of 330-385 nm (FIG. 7B). The white emission can be attributed to the broad fluorescence spectrum of the cross-linked product.

23


The cross-linking mechanism was investigated by UV and IR spectroscopies. The UV spectra of PI and PII exhibit a peak at ~340 nm associated with the π - π^* transitions of tris(4-triazolylphenyl)amine chromophores (FIG. 10). Their intensities decrease progressively with irradiation time, suggesting that part of the triazole rings of the polymer is opened. FIGS. 8 and 9 show the IR spectra of the polymer films before and after UV irradiation. After the experiment, the azide absorption becomes weaker and a new broad peak, which can be assigned to the carbonyl group stretching vibration, appears at 1720 cm^{-1} . This means that a fraction of the polymer chains is photo-oxidized. Thus, the mechanism can be proposed as follows: the azides groups are first decomposed upon UV irradiation and then crosslink with triazoles moieties, then part of the triazoles are oxidized after the ring-open.

Additionally, organometallic polytriazoles are easily obtained when the metal containing azido monomers or aroylacetylene monomers are reacted with aroylacetylenes or azido monomers, respectively, which will serve as precursors for magnetic ceramics when pyrolyzed at elevated temperatures.

Furthermore, the hyperbranched polytriazoles may act as fluorescent adhesive materials with large tensile strength between two metals, such as copper, iron, or alumina. These are non-limiting examples, however, and other metals may be used.

EXAMPLE 1

Hyperbranched Polytriazole Constructed from tris(4-ethynylphenyl)amine and 1,4-bis(4-azidobutoxy)benzene (PI)




24

Into a 20 mL Schlenk tube with a stopcock in the sidearm were added tris(4-ethynylphenyl)amine (0.126 g, 0.4 mmol) and 1,4-bis(4-azidobutoxy)benzene (0.183 g, 0.6 mmol). The tube was evacuated and refilled with nitrogen three times through the side arm. Then freshly distilled 1,4-dioxane (3.5 mL) was injected. The mixture was refluxed for 72 h. After cooled down to room temperature, the solution was diluted with small amount of chloroform and then added dropwise to 300 mL hexane/chloroform mixture (10:1, v/v) through a cotton filter under stirring. The precipitation was collected and dried to constant weight in vacuum.

Characterization data: Yellow powder; yield: 64.0%. M_w 5500; M_w/M_n 2.0 (GPC, polystyrene calibration). 1,4-disubstituted 1,2,3-triazole content (53%). IR (KBr), ν (cm^{-1}): 3283, 2097, 1606, 1557, 1506, 1227, 825. ^1H NMR (300 MHz, DMSO-d_6), δ (ppm): 8.63, 8.00, 7.48, 7.21, 7.09, 6.93, 6.87, 4.54, 4.21, 4.00, 3.92, 2.08, 2.01, 1.74. ^{13}C NMR (75 MHz, DMSO-d_6), δ (ppm): 152.5, 145.9, 136.9, 133.1, 132.5, 129.7, 127.0, 126.5, 125.5, 124.8, 123.8, 123.4, 122.6, 121.0, 115.2, 83.4, 80.1, 67.1, 50.4, 49.3, 47.5, 26.5, 26.2, 26.0, 25.8, 25.6, 25.1, 24.7. Elem. Anal.: calcd (%): C, 70.65; H, 6.27; N, 15.84. Found (%): C, 70.46; H, 5.79; N, 17.28.

25
EXAMPLE 2

Hyperbranched Polytriazole by 1,3-dipolar
Cycloaddition of tris(4-ethynylphenyl)amine and
1,4-Bis(6-azidohexyloxy)benzene (PII)





This hyperbranched polytriazole was carried out in accordance with the same procedure as described in Example 1 with tris(4-ethynylphenyl)amine (0.126 g, 0.4 mmol) and 1,4-bis(4-azidobutoxy)benzene (0.216 g, 0.6 mmol).

Characterization data: Yellow powder; yield: 75.7%. M_w 11400; M_w/M_n 2.7 (GPC, polystyrene calibration). 1,4-disubstituted 1,2,3-triazole content (50%). IR (KBr), ν (cm^{-1}): 3286, 2095, 1601, 1556, 1506, 1491, 1228, 824. ^1H NMR (300 MHz, $\text{DMSO}-d_6$), δ (ppm): 8.60, 7.89, 7.51, 7.23, 7.09, 6.86, 4.47, 4.21, 3.88, 1.95, 1.83, 1.72, 1.63, 1.45, 1.39, 1.32. ^{13}C NMR (75 MHz, $\text{DMSO}-d_6$), δ (ppm): 152.5, 147.4, 146.7, 146.0, 136.7, 132.7, 132.3, 129.2, 126.5, 126.4, 125.0, 124.5, 124.3, 123.8, 123.2, 123.0, 122.8, 118.6, 115.0, 82.9, 67.8, 56.3, 50.8, 49.7, 47.6, 29.7, 29.4, 28.6, 28.5, 28.2, 25.9, 25.7, 25.1, 24.9. Elem. Anal.: Calcd (%): C, 72.33; H, 7.18; N, 14.06. Found (%): C, 72.18; H, 6.42; N, 16.05.

EXAMPLE 3

Hyperbranched Polytriazole by Polymerization of
1,3,5-triethynyl-2-(hexyloxy)benzene and 1,4-bis(4-
azidobutoxy)benzene (PIII)




This hyperbranched polymer was carried out in accordance with the same procedure as described in Example 1 with 1,3,5-triethynyl-2-(hexyloxy)benzene (0.125, 0.5 mmol) and 1,4-bis(4-azidobutoxy)benzene (0.228 g, 0.75 mmol).

Characterization data: Orange powder, yield: 47.9%. M_w 10600; M_w/M_n 2.7 (GPC, polystyrene calibration).

27
EXAMPLE 4

Hyperbranched Polytriazole by Polymerization of
1,3,5-triethynyl-2-(hexyloxy)benzene and 1,4-bis(6-
azidoheptyloxy)benzene (PIV)




This hyperbranched polymer was carried out in accordance
with the same procedure as described in Example 1 with
1,3,5-triethynyl-2-(hexyloxy)benzene (0.125, 0.5 mmol) and
1,4-bis(6-azidoheptyloxy)benzene (0.270 g, 0.75 mmol).

Characterization data: Orange power, yield: 62.8%. M_w
23800; M_w/M_n 4.3 (GPC, polystyrene calibration).

28
EXAMPLE 5

Hyperbranched Polytriazole by Polymerization of
1,3,5-triethynyl-2-(hexyloxy)benzene and
1,4-bis(azidomethyl)benzene (V)




This hyperbranched polymer was carried out in accordance
with the same procedure as described in Example 1 with
1,3,5-triethynyl-2-(hexyloxy)benzene (0.050 g, 0.2 mmol)
and 1,4-bis(azidomethyl)benzene (0.056 g, 0.3 mmol).

Characterization data: Orange power, yield: 71.7%. M_w
7100; M_w/M_n 3.2 (GPC, polystyrene calibration).


EXAMPLE 6

Polytriazole by Polymerization of 3,3'-(1,4-phenylenedimethoxy) bis(benzoylacetylene) with 1,4-bis(6-azidoheptyloxy)benzene (PVI)



29

30




3,3'-(1,4-phenylenedimethoxy)bis(benzoylacetylene) (0.118 g, 0.3 mmol) and 1,4-bis(6-azidohexyloxy)benzene (0.108 g, 0.3 mmol) were added to a Schlenk tube, then 1 mL DMF and 1 mL toluene were added subsequently. After the monomers were totally dissolved and the solution became transparent, the mixture was heated up to 100° C. and reacted at that temperature for 6 h. The solution was then diluted with a small amount of chloroform and added dropwise into 200 mL hexane through a cotton filter under stirring. The precipitation was collected and dried to constant weight in vacuum.

Characterization data: Yellow powder, yield: 92.0%. M_w 26700; M_w/M_n 2.0 (GPC, polystyrene calibration). 1,4-dis-

substituted 1,2,3-triazole content (88.5%). ^1H NMR (300 MHz, CDCl_3), δ (ppm): 8.23, 8.11, 8.03, 7.94, 7.48, 7.24, 6.78, 5.15, 4.75, 4.44, 3.87, 3.27, 1.99, 1.74, 1.43, 0.88. ^{13}C NMR (75 MHz, CDCl_3), δ (ppm): 185.37, 158.82, 153.24, 148.19, 137.98, 136.70, 129.70, 128.46, 128.06, 123.94, 120.98, 115.80, 115.61, 70.18, 68.48, 50.87, 30.47, 29.46, 26.60, 25.94.

EXAMPLE 7


Polytriazole by Polymerization of 3,3'-(1,4-phenylenedimethoxy) bis(benzoylacetylene) with 1,4-bis(4-azidobutoxy)benzene (PVII)



31

This polymer was carried out in accordance with the same procedure as described in Example 6 with 78.8 mg (0.2 mmol) of 3,3'-(1,4-phenylenedimethoxy) bis(benzoylacetylene) and 60.8 mg (0.2 mmol) of 1,4-bis(4-azidobutoxy)benzene in 0.6 mL DMF and 0.6 mL toluene mixture solvents.

Characterization data: white power, yield: 89.6%. M_w , 15900; M_w/M_n , 1.8 (GPC, polystyrene calibration). 1,4-disubstituted 1,2,3-triazole content (88.5%). ^1H NMR (300 MHz, CDCl_3), δ (ppm): 8.26, 8.07, 8.02, 7.94, 7.47, 7.23,



PVIII

35


This polymer was carried out in accordance with the same procedure as described in Example 6 with 0.112 g (0.3 mmol) of 3,3'-(1,4-1,6-hexylenedioxy)bis(benzoylacetylene) and 0.108 g (0.3 mmol) of 1,4-bis(6-azidohexyloxy)benzene in 1 mL DMF and 1 mL toluene mixture solvents.

Characterization data: yellow solid, yield: 83.7%. M_w , 19100; M_w/M_n , 1.8 (GPC, polystyrene calibration). 1,4-disubstituted 1,2,3-triazole content (89.3%). ^1H NMR (300 MHz, CDCl_3), δ (ppm): 8.24, 8.06, 8.00, 7.92, 7.41, 7.15, 6.78, 4.75, 4.44, 4.06, 3.87, 3.27, 1.99, 1.74, 1.56, 1.44. ^{13}C NMR (75 MHz, CDCl_3), δ (ppm): 185.22, 158.92, 152.92, 147.93, 137.59, 129.25, 128.10, 123.17, 120.37, 115.28, 115.10, 68.16, 68.04, 50.53, 30.15, 29.21, 29.15, 26.28, 25.94, 25.61.

50


EXAMPLE 9

Polytriazole by Polymerization of 3,3'-(1,6-hexylenedioxy)bis(benzoylacetylene) with 1,4-bis(4-azidobutoxy)benzene (PIX)



33

34



20


This polymer was carried out in accordance with the same procedure as described in Example 6 with 74.9 mg (0.2 mmol) of 3,3'-(1,4-1,6-hexylenedioxy)bis(benzoylacetylene) and 60.8 mg (0.2 mmol) of 1,4-bis(4-azidobutoxy)benzene in 0.6 mL DMF and 0.6 mL toluene mixture solvents.

Characterization data: yellow solid, yield: 91.2%. M_w 23700; M_w/M_n 2.1 (GPC, polystyrene calibration). 1,4-disubstituted 1,2,3-triazole content (89.3%). ^1H NMR (300 MHz, CDCl_3), δ (ppm): 8.27, 8.04, 7.91, 7.40, 7.16, 6.79, 4.81, 4.52, 4.05, 3.93, 3.35, 2.17, 1.83, 1.56, 1.27, 0.88. ^{13}C NMR (75 MHz, CDCl_3), δ (ppm): 185.52, 159.23, 153.09, 148.23, 137.90, 129.59, 128.58, 123.46, 120.68, 115.62, 115.54, 68.36, 67.71, 50.64, 29.53, 27.59, 26.55, 26.25.

35

EXAMPLE 10


Polytriazole by Polymerization of 4,4'-(ethylene-dioxydiethoxy) bis(benzoylacetylene) with 1,4-bis(6-azidohexyloxy)benzene (PX)



35

This polymer was carried out in accordance with the same procedure as described in Example 6 with 0.122 g (0.3 mmol) of 4,4'-(ethylenedioxydiethoxy) bis(benzoylacetylene) and 0.108 g (0.3 mmol) of 1,4-bis(6-azidoheptyloxy)benzene in 1.0 mL DMF and 1.0 mL toluene mixture solvents.

Characterization data: yellow solid, yield: 90.3%. M_w 8800; M_w/M_n 1.6 (GPC, polystyrene calibration).



36

EXAMPLE 11


Polytriazole by Polymerization of 4,4'-(ethylene-dioxydiethoxy) bis(benzoylacetylene) with 1,4-bis(4-azidobutoxy)benzene (PXI)

This polymer was carried out in accordance with the same procedure as described in Example 6 with 81.3 mg (0.2 mmol) of 4,4'-(ethylenedioxydiethoxy) bis(benzoylacetylene) and 60.8 mg (0.2 mmol) of 1,4-bis(4-azidobutoxy)benzene in 0.6 mL DMF and 0.6 mL toluene mixture solvents.


Characterization data: yellow solid, yield: 49.1%. M_w 9100; M_w/M_n 1.7 (GPC, polystyrene calibration).

EXAMPLE 12

Polytriazole by Polymerization of N,N-bis(4-ethynylcarbonylphenylene)aniline with 1,4-bis(azidomethyl)benzene (PXII)



-continued




PXII

This polymer was carried out in accordance with the same procedure as described in Example 6 with 54.6 mg (0.15 mmol) of N,N-bis(4-ethynylcarbonylphenyl)aniline and 29 mg (0.15 mmol) of 1,4-bis(4-azidomethyl)benzene in 0.7 mL DMF and 0.7 mL toluene mixture solvents.

Characterization data: yellow solid, yield: 93.3%. 1,4-disubstituted 1,2,3-triazole content (89.3%). ¹H NMR (300 MHz, CDCl₃), δ (ppm): 8.36, 8.19, 8.04, 8.01, 7.74, 7.36, 7.17, 5.94, 5.61, 4.36, 3.38. Quantum yield in 1,4-dioxane: 45.3% (quinine sulfate in 0.1 NH₂SO₄ is selected as calibrate).

EXAMPLE 13

Polytriazole by Polymerization of N,N-bis(4-ethynylcarbonylphenyl)aniline with 1,4-bis(4-azidobutoxy)benzene (PXIII)




PXIII

This polymer was carried out in accordance with the same procedure as described in Example 6 with 70.0 mg (0.2 mmol) of N,N-bis(4-ethynylcarbonylphenyl)aniline and 60.8 mg (0.2 mmol) of 1,4-bis(4-azidobutoxy)benzene in 0.6 mL DMF and 0.6 mL toluene mixture solvents.

Characterization data: Yellow solid; 95.1% yield. M_w , 13 700; M_w/M_n 1.8 (GPC, polystyrene calibration). 1,4-disubstituted 1,2,3-triazole content (90.4%). IR (KBr), ν (cm⁻¹): 2950, 2871, 2096, 1641, 1583, 1505, 1233, 1178. ¹H NMR (300 MHz, CDCl₃), δ (TMS, ppm): 8.45, 8.31, 8.01, 7.82, 7.37, 7.21, 6.80, 4.80, 4.54, 3.95, 3.35, 2.19, 1.82. ¹³C NMR (75 MHz, CDCl₃), δ (ppm): 183.82, 152.94, 151.19, 148.39, 145.74, 132.34, 130.85, 129.89, 128.13, 126.93, 122.30, 115.39, 115.31. Quantum yield in THF: 49% (quinine sulfate in 0.1 NH₂SO₄ is selected as calibrate).

Polytriazole by Polymerization of
N,N-bis(4-ethynylcarbonylphenyl)aniline with
1,4-bis(6-azidohexyloxy)benzene (PXIV)



PXIV

This polymer was carried out in accordance with the same procedure as described in Example 6 with 70.0 mg (0.2 mmol) of N,N-bis(4-ethynylcarbonylphenyl)aniline and 72.1 mg (0.2 mmol) of 1,4-bis(6-azidohexyloxy)benzene in 0.6 mL DMF and 0.6 mL toluene mixture solvents.

Characterization data: Yellow solid; 90.2% yield. M_w 14 400; M_w/M_n 1.8 (GPC, polystyrene calibration). 1,4-disubstituted 1,2,3-triazole content (88.4%). IR (KBr), ν (cm^{-1}): 2939, 2862, 2095, 1638, 1583, 1505, 1233, 1177. ^1H NMR (300 MHz, CDCl_3), δ (TMS, ppm): 8.46, 8.25, 8.00, 7.83, 7.37, 7.19, 6.79, 4.73, 4.46, 3.89, 3.28, 2.01, 1.76, 1.45. ^{13}C NMR (75 MHz, CDCl_3), δ (ppm): 183.87, 153.07, 151.20, 148.40, 145.76, 132.37, 130.86, 129.89, 127.99, 126.94, 125.75, 122.32, 115.36, 68.15, 50.50, 30.10, 29.08, 26.21, 25.54. Quantum yield in THF: 53% (quinine sulfate in 0.1 N H_2SO_4 is selected as calibrate).

TABLE 1

Effect of Solvent on Thermal Click Polymerization ^a					
entry	solvent	time (h)	yield (%)	M_w^b	M_w/M_n^b
1	toluene	90	trace	1 900	1.3
2	tetralin	90	31.0	5 100	2.1
3	chlorobenzene	77	39.2	3 900	1.7
4	o-DCB ^c	77	50.1	5 200	1.9
5	1,4-dioxane	77	79.7	5 800	2.3

^aCarried out at 110° C. under nitrogen; the molar ratio of tris(4-ethynylphenyl)amine and 1,4-bis(4-azidobutoxy)benzene is 2:3; the concentration of tris(4-ethynylphenyl)amine is 0.067 M (entries 1 and 2) and 0.1 M (entries 3-5).

^bDetermined by GPC in THF on the basis of a polystyrene calibration.

^co-DCB = 1,2-dichlorobenzene.

EXAMPLE 15

Tensile Test of Hyperbranched Polytriazoles
Between Two Metal Plates.

Tris(4-ethynylphenyl)amine (0.05 mmol) and 1,4-bis(6-azidohexyloxy)benzene (0.05 mmol) were dissolved in 0.1 mL of THF. The solution was then dropped onto the metal (copper, aluminum, iron) sample cell (1.2 inch) and then covered with another plate. The whole cells were put into oven to cure at 100° C. overnight. The area for loading cell is 25.4 mm×25.4 mm and the test speed is 2.0 mm/min. The mechanical data are shown in Table 4.

TABLE 2

Characterization of Hyperbranched Polytriazoles ^a					
monomers	yield (%)	M_w^b	M_w/M_n^b	T_d^c (° C.)	Φ_F^d (%)
I	64.0	5 500 (8 200)	2.0 (2.3)	405	38
II	75.7	11 400 (16 000)	2.7 (4.3)	402	43

^aCarried out in 1,4-dioxane at refluxing temperature under nitrogen for 72 hours; the monomers are tris(4-ethynylphenyl)amine and 1,4-bis(4-azidobutoxy)benzene in a molar ratio of 2:3; the concentration of tris(4-ethynylphenyl)amine is 0.12 M.

^bMeasured in THF by GPC and LS (data given in the parentheses).

^cTemperature at which 10% weight loss was recorded by TGA.

^dFluorescence quantum yield measured in DCM using 9,10-diphenylanthracene in cyclohexane ($\Phi_F = 90\%$) as standard.

41

42

TABLE 3


Characterization of linear poly(aroyltriazole)s ^a				
polymer	M _w	M _w /M _n	yield (%)	1,4-conf. (%) ^b
PVI	26 700	1.99	92.0	88.5
PVII	15 900	1.77	89.6	88.5
PVIII	19 100	1.80	83.7	89.3
PIX	23 700	2.09	91.2	89.3


^aReacted at 100° C. for 6 hour; [M] = 0.15 M.^b1,4-conf. means the percentage of 1,4-disubstituted 1,2,3-triazoles inside the polymers.

TABLE 4

Mechanical properties of metal plates adhered by hyperbranched Polytriazoles.				
Metal	Peak load (N)	Peak stress (MPa)	Strain at break (mm/mm)	Modulus (MPa)
Cu	652.1	1.0	0.020	57.0
Al	360.8	0.6	0.038	16.4
Fe	295.0	0.5	0.028	22.6


Chart 1







45

46




What is claimed is:

1. A process for the synthesis of poly(aryltriazoles), comprising: reacting separate azide monomers and acetylene monomers by 1,3-dipolar cycloaddition, wherein one of the azide monomers and acetylene monomers is a di-monomer and the other monomer is a tri-monomer, and wherein polymerization occurs by refluxing said monomers in an organic solvent; wherein the acetylene monomer has formula II or IV:



wherein R_1 is



25

30

(II)


35

40

(IV)

45


50



R is an alkyl, a vinyl, an acetyl, an aryl or a heteroaryl.

2. The process according to claim 1, wherein the azide monomers are selected from the group consisting of diazides, conjugated diazides, nonconjugated diazides, triazides, conjugated triazides, nonconjugated triazides, metal containing diazides, metal containing conjugated diazides, metal containing nonconjugated diazides, metal containing triazides, metal containing conjugated triazides and metal containing nonconjugated triazides.

3. The process according to claim 1, wherein the azide monomer has formula V or VI:







(V)




65

47

-continued

wherein R_2 is

Ar is

 $m > 1$; R_3 is

X is hydrogen, an alkyl, a vinyl, an acetyl, an aryl, a heteroaryl, or a halogen; and

R is an alkyl, a vinyl, an acetyl, an aryl or a heteroaryl.

4. The process according to claim 1, wherein the organic solvent is selected from the group consisting of 1,4-dioxane, dimethylformamide, toluene, and mixtures thereof.


5. The process according to claim 1, wherein said polymerization occurs for about 4 to about 6 hours.

6. A polytriazole prepared by the process according to claim 1, wherein the poly(aryltriazole) has the formula IX:


48

(VI)




(IX)




wherein

 R_1 is


R is an alkyl, a vinyl, an acetyl, an aryl, or a heteroaryl;

 R_2 is



Ar is



49

and $m > 1$.

7. A poly(aryltriazole) prepared by the process according to claim 1, wherein the poly(aryltriazole) has the formula X:

 R_3 is

50

R is an alkyl, a vinyl, an acetyl, an aryl, or a heteroaryl;

X is hydrogen, an alkyl, a vinyl, an acetyl, an aryl, a heteroaryl, halogen;

 R_4 is

5

10


15

20

25

(X)

8. A process for the synthesis of poly(aryltriazoles), comprising: polymerizing separate diazide monomers and aroyldiacetylene monomers by 1,3-dipolar cycloaddition wherein polymerization occurs by refluxing said monomers in an organic solvent; wherein the diazide monomer has formula XI:



(XI)

30



wherein

 R_2 is

35

40

45





R is an alkyl, a vinyl, an acetyl, an aryl, or a heteroaryl;

 Ar is

50

55

60


 $m > 1$.

65

9. The process according to claim 8, wherein the aroyldiacetylene monomers are selected from the group consisting of aroyldiacetylenes and metal containing aroyldiacetylenes.


51

10. The process according to claim 8, wherein the aroyldi-acetylene monomer has formula XII:



wherein

R₄ is




and

R is hydrogen, an alkyl, a vinyl, an acetyl, an aryl or a heteroaryl.


11. The process according to claim 8, wherein the organic solvent is selected from the group consisting of 1,4-dioxane, dimethylformamide, toluene, and mixtures thereof.

12. The process according to claim 8, wherein the poly (aroyltriazoles) are compounds of formula XIII:




wherein

R₂ is $-(CH_2)_m-Ar-(CH_2)_m-$, or



Ar is $-O-C_6H_4-O-$, $-C_6H_4-$,




, or


52

-continued

(XII) 5




10




R₄ is $-C_6H_4-(CH_2)_m-C_6H_4-$,


15




20




25




30




35




(XIII) 40




45




50



55



60




65

R is, an alkyl, a vinyl, an acetyl, an aryl or a heteroaryl; and
m > 1.


53

13. A poly(aryltriazole) prepared by the process of claim 8, wherein the poly(aryltriazole) has the formula XIV:



54

-continued



R is hydrogen, an alkyl, a vinyl, an acetyl, an aryl or a heteroaryl; and
m > 1.

14. The process according to claim 1, wherein the comonomers are mixed together in dimethylformamide and optimally an additional solvent selected from the group consisting of toluene, dioxane, and benzene.

15. The process according to claim 1, wherein the comonomers are mixed in dimethylformamide and toluene.

16. The process according to claim 15, wherein the dimethylformamide and toluene are present in a ratio of 1:1 (volume:volume).

17. The process according to claim 14, wherein the comonomers are reacted at 0-200° C. for 1-24 hours.

18. A light emissive polymer synthesized by the process according to claim 1.

* * * * *

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : 7,772,358 B2
APPLICATION NO. : 11/896675
DATED : August 10, 2010
INVENTOR(S) : Benzhong Tang, Anjun Qin and Matthias Haeussler

Page 1 of 2


It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

Claim 7, Column 50, Lines 5-20:

Please delete:

"R₄ is


"



and replace with:

-- R₄ is

--




Signed and Sealed this

Twenty-sixth Day of October, 2010

David J. Kappos

David J. Kappos
Director of the United States Patent and Trademark Office

Claim 12, Column 52, Lines 35-39:
Please delete:



and replace with:

